SPRADLING®

Dolce™

COMMERCIAL SPECIFICATION

GENERAL

Weight	340 ± 10% g/m²
Width	1.37 m
Roll Length	27.4 m
Composition	PU
Gauge	0.8 ± 10% mm

BACKING

Description	100% Rayon
Weight	180 None - None

SUSTAINABLE PRODUCT PROFILE

ATTRIBUTES

No Heavy Metals	EN 71-3 CERTIFICATE

SUSTAINABLE MANUFACTURING CERTIFICATIONS

COMPLIANCES

REACH COMPLIANT RoHS COMPLIANT

ADDITIONAL TESTS

Tensile Strength Test - ISO 13934-1

N/3cm(Min.)	Warp	≥200
	Fill	≥200

Elongation I Test AT - ISO 13934-1

%	Warp	≥10
	Fill	≥15

Tear Strength Test - ISO 4674-1 MB

N(Min.)	Warp	20
	Fill	20

Seam Strength Test - ISO 13935-2

(Min.)	Warp	≥180
	Fill	≥180

Adhesion Test - ASTM D751

N/3cm(Min.)	Warp	≥18
	Fill	≥18

Abrasion Resistant II Test - ASTM D4157

WYZENBEEK		≥ 100,000 Cycles

Crocking Resistant I Test (AATCC 8)

---------	Wet	4
	Dry	4

Flex Resistance Test - ISO 5402

cycles(Min.)	Warp	25,000 = Passes
	Fill	

UV stability Test

Quv	ASTM D1148	300 w 24h = 4.0 rating

Blocking Test

FTMS 191A-M5872 / CFFA-4	82°C 30 minutos = No 1 - No Blocking

FLAME RETARDANCY

BS 5852 - UNITED KINGDOM - Source 0	Pass
EU/US IMO FTPC Part 8	Pass
US FMVSS 302	Pass

US CAL TB 117-2013, Section 1	Pass
EU EN 1021 Part 1 & 2	Pass

This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.

OTHER ATTRIBUTES

Hydrolisis Resistant Method	ISO 1419 MC
Polycarbonate Resins	Yes
No Heavy Metals	Yes

Formaldehyde Free	Yes
Antistatic	Yes

WARRANTY

*Terms and Conditions apply.

Note: The data correspond to minimum results of the statistical analysis. The information included in the specification is subject to change.
The indicated data corresponding to the material's physical characteristics are results of test conducted under standard procedures and are subject to variation. We therefore recommend our customers to evaluate the material with regard to the specific requirements and application(s) before specifying. For additional information, please contact your sales representative.
These terms and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.
Spradling group does not assume any responsibility for any damages resulting from improper applications.
Spradling group does not guarantee exact color matches as slight variations in production and stock may occur, as such lot separations is suggested.
Spradling group reserves the right to modify technical sheets without notification.

For a better experience, we recommend opening the file directly in a PDF viewer, and not in the browser.

Conscious of our impact. Designed for the long run.

SPRADLING®
For the long run

V. 10 | Date: August 19, 2021