

TATAMI

Artificial leather for sport mats

Fabric Description

Type	635	660	725
Composition:	PVC / PES	PVC / PES	PVC / PES
Fabric weight (g/m ²):	635 ± 30	670 ± 30	730 ± 30
Thickness (mm):	1,3 ± 0,1	1,2 ± 0,12	1,2 ± 0,12
Usable width (cm):	97 ± 1	125 ± 1	140 ± 3

Certificates

Test description	Certification	Value		
Type		635	660	725
Tensile strength warp/weft (N / 2cm):	CSN 64 7012	120 / 60	600 / 300	100 / 70
Ultimate elongation warp/weft (%):	CSN 64 7012	60 / 140	20 / 20	50 / 100
Tear strength warp/weft (N):	CSN 64 7032	15 / 15	150 / 150	25 / 20
Cohesion of layers (N.m ⁻¹):	CSN 64 7030	500	500	350
Resistance to blending on 23°C (kilocycles / deg / deg):	CSN 64 7029	5 / 4 / 4	5 / 5 / 5	10 / 4 / 4
Abrasion resistance on 44 kPa, elongation 5%, dry (cycles / deg / deg):	CSN 64 7031	-	300 / 4 / 4	1000 / 4 / 4
Abrasion resistance on 44 kPa, elongation 5%, wet (cycles / deg / deg):	CSN 64 7031	-	250 / 4 / 4	500 / 4 / 4
Suitability temperature range (°C):		-5 to +40	-20 to +60	-5 to +40

The product is Phthalate free (do not contain: DEHP, BBP, DBP, DIBP, DINP, DIDP, DNOP).

The product has REACH certificate.

Place of origin : EU

Cleaning

- Use only disinfectants suitable for plastic surfaces.
- The disinfectants should not be changed.
- The resistance to disinfectants which are manufactured outside of the EU has to be examined in each case.

Date: 2024.02.11.